

PHENGUARD 965

4 pages

 March 2011
 Revision of April 2009

DESCRIPTION	two component high build amine adduct cured novolac phenolic epoxy coating	
PRINCIPAL CHARACTERISTICS	<ul style="list-style-type: none"> – Phenguard 965 system – excellent resistance to a wide range of organic acids, alcohols, fats (regardless of free fatty acid content) and solvents – maximum cargo flexibility – low cargo absorption – easy to clean – good resistance to hot water – can be applied and cures at temperatures down to +5°C – good application properties, resulting in a smooth surface 	
COLOURS AND GLOSS	offwhite, pink, grey - eggshell	
BASIC DATA AT 20°C	(1 g/cm ³ = 8.25 lb/US gal; 1 m ² /l = 40.7 ft ² /US gal) (data for mixed product)	
Mass density	1.7 g/cm ³	
Volume solids	68 ± 2%	
VOC (supplied)	max. 195 g/kg (Directive 1999/13/EC, SED) max. 329 g/l (approx. 2.7 lb/gal)	
Recommended dry film thickness	100 µm *	
Theoretical spreading rate	6.8 m ² /l for 100 µm *	
Touch dry after	2 - 3 hours at 20°C, 14 - 16 hours at 5°C	
Overcoating interval	min. 8 hours * max. 14 days *	
Full cure after	see curing table *	
	(data for components)	
Shelf life (cool and dry place)	at least 12 months * see additional data	
RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES	<ul style="list-style-type: none"> – steel; blast cleaned in situ to at least ISO-Sa2½ and free from rust, scale, shop primer and any other contamination – blasting profile 50 - 100 µm – the substrate must be perfectly dry before and during application of Phenguard 965 – substrate temperature must be above 5°C and at least 3°C above dew point during application and curing 	
SYSTEM SPECIFICATION	Phenguard 965 offwhite	100 µm
	Phenguard 965 pink	100 µm
	Phenguard 965 grey	100 µm

PHENGUARD 965

March 2011

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 87 : 13

- the temperature of the mixed base and hardener should preferably be above 15°C, otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance
- thinner should be added after mixing the components

Induction time

allow induction time before use
 5°C - 20 min.
 10°C - 15 min.
 15°C - 10 min.

Pot life

2 hours at 20°C *
 * see additional data

AIRLESS SPRAY

Recommended thinner
 Volume of thinner
 Nozzle orifice
 Nozzle pressure

Thinner 91-92
 5 - 10%, depending on required thickness and application conditions
 approx. 0.46 - 0.53 mm (= 0.018 - 0.021 in)
 15 MPa (= approx. 150 bar; 2130 p.s.i.)

AIR SPRAY

Recommended thinner
 Volume of thinner
 Nozzle orifice
 Nozzle pressure

Thinner 91-92
 5 - 10%, depending on required thickness and application conditions
 2 mm
 0.3 MPa (= approx. 3 bar; 43 p.s.i.)

BRUSH/ROLLER

Recommended thinner
 Volume of thinner

Thinner 91-92
 0 - 5%

CLEANING SOLVENT

Thinner 90-53

SAFETY PRECAUTIONS

for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets

 this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

ADDITIONAL DATA

Film thickness and spreading rate

theoretical spreading rate m ² /l	6.8	5.4
dft in µm	100	125

max. dft when brushing:

60 µm

PHENGUARD 965

March 2011

Overcoating table for Phenguard 965 for dft up to 100 µm

substrate temperature	5°C	10°C	15°C	20°C	30°C
minimum interval	24 hours	20 hours	14 hours	8 hours	6 hours
maximum interval	28 days	25 days	21 days	14 days	7 days

- surface should be dry and free from any contamination

Curing table for dft up to 100 µm

substrate temperature	min. curing time of Phenguard 965 system before transport of cargoes without note 4, 7, 8 or 11 and ballast water and tanktest with sea water
5°C	7 days
10°C	5 days
15°C	4 days
20°C	3 days
30°C	2 days

- minimum curing time of Phenguard 965 system before transport of cargoes with note 4, 7, 8 or 11: 3 months
- for detailed information on resistance and resistance notes, please refer to the latest issue of the Cargo Resistance List
- for transport of methanol and vinyl acetate monomer, a hot cargo cure is required which cannot be substituted by a service period of 3 months with non-aggressive cargoes
- adequate ventilation must be maintained during application and curing (please refer to sheets 1433 and 1434)
- when used as a primer under solvent free tank-linings the dft must be limited to a maximum of 100 µm

Pot life (at application viscosity)

5°C	8 hours
10°C	6 hours
15°C	4 hours
20°C	2 hours
30°C	1 hour

PHENGUARD 965

March 2011

Worldwide availability

Whilst it is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434
Cleaning of steel and removal of rust	see information sheet 1490

LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the Sigma Coatings products made by PPG Protective & Marine Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

PPG Protective & Marine Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. PPG Protective & Marine Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development.

This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.

The English text of this document shall prevail over any translation thereof.

	PDS	7959
199289	offwhite	7001002200
199282	pink	6007002200
199284	grey	5000002200